



FLSMIDTH WEAR MAX[®] epoxy ceramic coating

When your situation demands a quick, hard-wearing solution, you can depend on FLSMIDTH WEAR MAX[®] epoxy ceramic coating.

Protect your equipment

Fabricated from a proprietary mixture of epoxy and wear resistant ceramic beads, WEAR MAX[®] combines the hard-wearing properties of ceramic with bonding properties of epoxy cost-effectively. WEAR MAX is proven to reduce abrasion wear problems commonly occurring in bulk handling and processing equipment.

WEAR MAX is applicable to any surface where sliding abrasion causes wear on pipes, chutes, silos, tanks, casings and many other equipment. It adheres effectively to most clean and dry surfaces including metal, ceramic, rubber and concrete. Its fast cure rate results in a quick turnaround time, increased uptime for repairs and overall cost savings.

WEAR MAX is supplied in conveniently sized packs, complete with all necessary mixing equipment. It may be your site's handiest toolkit.

Increase uptime and productivity

WEAR MAX® packaging

Our WEAR MAX® comes in a twin kit pack containing two 7 kg (15 lb) buckets of WEAR MAX Part A bead/resin mixture and two graduated plastic bottles each containing 250 mL (8.5 oz) of the Part B liquid hardener. The kit is complete with two pairs of nitrile gloves, a mixing board and spatula so you are ready for on-site mixing and application.

WEAR MAX® working time and cure time

FLSmidth WEAR MAX® has a working time (pot life) of approximately 15 minutes after being thoroughly mixed and is hard cured in four hours. It reaches its maximum hardness after curing for 24 hours, based on an ambient temperature of 23°C (73°F).

The Part B liquid hardener is graduated into quarters so that if only a part of the kit is to be used, it is easy to measure the correct ratio of Part A and Part B.

Typical cured property

Working time	15 minutes
Hard cure time	4 hours
Maximum hardness time	24 hours at 23°C (73°F)
Maximum operation temperature	70°C (158°F)
Density	2.1 kg/l (17.5 lb/gal.)
Compression strength	70 MPa
Tensile strength	10 MPa
Flexural strength	15 MPa
Coverage 7kg @ 12 mm thickness	0.275 m ² (2.9 sq. ft.)
Minimum shelf life (unopened)	2 years



Applying WEAR MAX® to centrifuge housing

Common applications

- Chutes and surfaces worn by sliding abrasion
- Pipes, elbows, T-junctions and launders worn by abrasive slurries
- Chutes where moderate impact is present
- Paste backfill applications
- Any surface where sliding abrasion causes wear on: centrifuges, screen bowels, vibrating screens, thickeners, tanks, silos, chutes and pipes

FLSmidth Pty Ltd
Pinkenba QLD 4008
Australia
Tel: +61 7 3121 2900
Email: info.australia@flsmidth.com

FLSmidth USA Inc.
Midvale, UT 84047
USA
Tel: +1 801 871 7000
Email: info.usc@flsmidth.com

FLSmidth Chile
Santiago, Chile
CPN
Tel: +56 2 2290 0000
Email: info.chile@flsmidth.com

FLSmidth Private Limited
Chennai, Tamil Nadu
India
Tel: +91-44-4748 1000
Email: indiainfo@flsmidth.com

www.flsmidth.com

Copyright © 2021 FLSmidth A/S. ALL RIGHTS RESERVED. FLSmidth is a (registered) trademark of FLSmidth A/S. This brochure makes no offers, representations or warranties (express or implied), and information and data contained in this brochure are for general reference only and may change at any time.

M 05-21 7000-4-ENG